



A REVIEW - EFFECT OF PARAMETERS AND ITS ANALYSIS ON FORMABILITY

Dr. Shailendra Dwivedi¹, Ashwin Kumar Bhaisare², Anil Singh³

¹*Department of Mechanical Engineering, Lakshmi Narain College of Technology, Bhopal (India)*

^{2,3}*Department of Mechanical Engineering, Lakshmi Narain College of Technology Excellence, Bhopal (India)*

ABSTRACT

In this review paper studied has been carried out the parameters those affects sheet metal formability and also about forming limit diagram (FLD). The parameters are punch nose radius, blank temperature, die arc radius, punch velocity, blank holding force (BHF), blank shape, spring back etc. In the first section of this paper shows the studies about formability. In the second section in the paper shows the studies about different parameters that affect sheet metal forming. Formability of sheet metal defined in terms of two dimensional strain maps and it also describes state of strain measures formability. This research paper deals with different research work those related to with forming limit diagram (FLD). The forming limit diagram gives an indication whether the material can sustain certain ratio of strains without failure.

Keywords: *Forming limit diagram, Sheet metal formability Blank holding force.*

I. INTRODUCTION

The forming process of metals into desired shapes and dimensions are almost the oldest fabricating technique. The sheet metal forming process is an economical method of manufacturing components because loss of material is too less. By this process, in which the required shapes and size of components are obtained through the plastic deformation of metal. Sheet metals are widely used for industrial because of its capacity for being bent and formed into intricate shapes. Sheet metal parts comprise a large fraction of automotive, agricultural machinery, and aircraft and aviation industries components as well as domestic and industrial consumer appliances.

II. FORMING PARAMETERS

Sheet metal forming operation depends on the selection of punch nose radius, die arc radius, punch velocity, blank holding force, spring back, blank size and shape, die clearance and proper selection of lubrication for the smooth and defect free operation. Forming limit diagram (FLD) and circle grid analysis helps to understand forming in sheet metals. The above mention process parameters and their contribution summary of some of the potential works have been discussed herein terms of analytical approach and experimental approach.



2.1 Punch Nose Radius

Waleed K. et.al (2008) studied the effect of punch nose radius on deep drawing operation. In this research work, six types of punches had been taken with various nose radii used to form a cylindrical cup of (44mm) outer diameter,(28mm) height, and(0.5mm)sheet thickness of mild steel of (0.15%) carbon content. A commercially finite element program code (ANSYS 5.4), were used to perform the numerical simulation of the deep drawing operation, and the numerical results were compared with the experimental work. The results show that, to form parts with large nose radii is much more than the value required forming parts with small punch nose radii. The greatest thinning is seen to occur with hemispherical punch (Dome shaped punch) due to great stretching of the metal over the punch head. The maximum tensile stresses and the maximum thinning of the dome wall occur nearly at the apex of the dome. This trends and observation has been validated by others authors also.

2.2. Blank Temperature

Venkateswarlu G., et al (2010) extensively studied formability aspects of aluminum 7075 to develop useful components of complex shapes. In this research study, the significance of three important process parameters of deep drawing namely blank temperature, die arc radius and punch velocity on the deep drawing characteristics of aluminum 7075 sheet werestudied. Author also applied the finite element method (FEM) and Taguchi analysis used to determine the influence of process parameters. Simulations were carried out as per orthogonal array using DEFORM 2Dsoftware. The predicted deformation of deep drawn cup and analysis of variance test (Anova), Author were observed that blank temperature has greatest influence on the formability of aluminum material followed by punch velocity and die arc radius.

2.3. Blank Holding Force

Marumo Y.et al(2007) has carried out the study regarding variation in the blank holding force required for the studied the behavior of wrinkling and the limiting drawing ratio with sheet thickness. Authors found that blank holding force required for the elimination of wrinkling increased rapidly as the sheet thickness decreased. When the sheet thickness was very thin, the blank holding force was strongly influenced by the coefficient of friction. The limiting drawing ratio decreased as sheet thickness decreased and it decreased rapidly below 0.04 mm thickness. When the sheet thickness was very thin, the limiting drawing ratio was strongly influenced by the coefficient of friction.

2.4 Initial Blank Shape

AhmetogluM.et al(1995)have been carried out the study of effect of process parameters such as initial blank shape and the blank holding force on the final part quality such as wrinkling and fracture in the product. During the initial experiments, it was found that the oval blank shape had the worst formability, from the damage and fracture point of view, among the three blank shapes oval, oblong, and rectangle have been considered and silent conclusion have been drawn. The oval shape reduced the fracture limit of AA 2008-T4. However, it caused smaller wrinkling heights in the flange along the sides of the rectangular pan. Control of the BHF as a function of time improves the formability and the quality of the final part. However, BHF control in time is not enough by itself. Since the deformation characteristics are not uniform around the periphery of the rectangle, the BHF has to be controlled as a function of location. Metal flow can be controlled by using draw beads on the sides of the rectangle for producing the quality defect free product. The similar study has been carried out by Fahretting



Ozturk (2004) in terms of ductile failure criteria in the product. In this study author keenly observe the behavior of stress and strain during the deformation and related to the forming limit diagram and given the contributory observation of the failure of the fracture in the product.

2.5 An Optimization Strategy for the Blank Holder Force (BHF)

GharibH.et al (2006) has been proposed an optimization strategy for the blank holder force for minimizes the maximum punch force and avoids process limits. That strategy was applied to the linearly varying BHF and compared to the constant BHF. They found that the optimized linear BHF resulted in an improved cup forming when compared to that produced by the constant BHF scheme. The BHF are optimized for different cases of drawing ratios and die coefficients of friction in order to analyze the nature of the optimum linear BHF scheme. It was found that the slope of the linear BHF scheme increases with the increase in the drawing ratio in a linear manner. Also, the intercept of the function showed a nearly linear variation with the drawing ratio. A general equation is deduced for the optimum blank holder force at any drawing ratio for the cup under study.

2.6 Spring Back

The tendency of spring back during the sheet metal forming process has been studied by many authors and as well given the contributory and remarkable conclusion for reducing the defect such as wrinkling, earing, damage, crack and fracture. Some research work which had been discussed at here. W.M. Chan, H.I. Chew, H.P. Lee, B.T. Cheok (2004) have presented a study of spring-back in the V-bending metal forming process with one clamped end and one free end. They found that spring-back occurs at the die-lip and V-region of the die model. Different die punch parameters such as punch radius, punch angle and die-lip radius were varied to study their effect on spring-back. Also, the effect of the punch displacement on spring-back was investigated. The H-convergence test was done to justify the number of elements used. Softwares used are Patran, Abaqus/Standard and Abaqus/CAE. Patran was used to model the nodes of the sheet metal and rigid surfaces of the die, pad and punch. Abaqus/Standard is used to simulate the punching process. The results were analyzed using Abaqus/CAE. Their analysis shows that spring-back angle of the valley region decreased with increment of punch radius and punch angle and spring-back is dependent on punch radius, punch angle and die-lip radius. Lee K.P.et al (2002), Carden W.D et al (2002) authors carried on the research also the spring back tendency and given the unique conclusion. Authors observed that the as the blank force reduces by that material displacement have been flow and behavior of wrinkling have been reduced as well properly plastic deformation has been done this phenomena help to reduce the spring back. Carden (2002) described the method to measure the spring back process. FlavioCimolin (2008) carried on the study of, to modify pretending to obtain a different configuration at the end of the punch stroke, but in order that the final piece coincides with the desired one after the deformation due to springback. Empirical die compensation has nowadays been replaced by numerical simulation, but the inverse problem that needs to be solved is non-trivial since the transformation from the modified geometry of the die and the final piece obtained from it implies a very complex FEM simulation. In this work we set the whole process of springback compensation on solid physical and mathematical grounds. An optimization algorithm based on the Gauss-Newton method was proposed to deliver automatic die compensation and its performance was investigated.



circular grid system and FLD proposed by Keeler was the analysis of strain distributions in actual stampings to improve part quality and optimize die design (1968). Since Keeler's experiments continued to verify his earlier results, showing that the lowest formability exists under plane strain conditions, he proposed restricting the inward flow of metal from the flange in order to induce biaxial tensile strains, thereby increasing the forming limits. The preceding studies focused on the determination of forming limits solely in the region of biaxial tension. However, in 1968, Goodwin used a combination of cup- and tension-tests to obtain a failure band in both the negative and positive quadrants of minor strain, creating the general form of the forming-limit diagram. In order to reveal the effects of planar anisotropy on formability, Marciniak et al. performed an experimental study involving steel, aluminum, and copper (1973). These tests were performed under proportional-straining conditions, and showed that the forming limits were significantly different in the rolling direction compared with transverse direction. This demonstrated that the limit curve does not consist of mirror images which begin at the principal axes and meet at the state of equal biaxial tension; instead, the limit strains are generally somewhat greater in the rolling direction. A further investigation of variations in the forming limit diagram was conducted by Ghosh and Hecker, who concluded that the limit strains obtained in punch stretching operations were considerably higher than those resulting from in-plane stretching tests [1974,1978]. Their in-plane stretching tests employed the use of a polyethylene spacer on either side of the nose of a punch in order to induce in-plane deformation. They theorized that the friction and curvature present during punch stretching cause strain localization to take place at a much lower rate than for in-plane stretching. Up to this point, most work on constructing the forming-limit diagram had employed the use of grid strain analysis on actual automotive stampings or on test specimens deformed by punches of various geometries. In 1975, Hecker introduced a methodical approach involving the stretching of sheets of various widths over a hemispherical punch to obtain strain conditions ranging from uniaxial tension to balanced biaxial tension(1975). Using the onset of localized necking to define a single limit of failure, Hecker obtained a forming-limit curve lying mostly within the Keeler– Goodwin band. The advantage of his technique is the ability to determine an entire forming-limit curve with specimens of different widths and, or the use of different lubricants. An analytical model describing neck growth in sheet metals under various loading conditions, from which a predicted forming-limit diagram can be calculated, was subsequently developed by Lee and Zaverl(1982). Their results corresponded to those of the lower, in-plane forming limits. However, the analysis did not account for the effects of strain history and its influence on such properties as the plastic strain ratio.

IV. SUMMARY

The forming limit diagram (FLD) introduced by Keller and Goodwin probably the most widely used method for representing sheet metal formability and extensive literature has been proposed in the last decade. The forming limit diagram typically represents the maximum permissible range of major and minor strains that a typical sheet material can undertake without failure. The forming limit diagram is experimentally measured for each sheet material by placing a grid of circle on the sheet sample and then deforming the same. A comparison of the original and the extensions in the marked grids on the sheet sample provide an estimate of the major and minor strain of the sample. The permissible range of the major and minor strains is actually available for a wide range of sheet metals and used considerably for designing of deep drawing operations, in particular. Application of



FEM and numerical method also give the unique approach to solve the spring back tendency and as well study of defects in the product that will help to practicing the produce the defect free product in the industries.

REFERENCES

- [1] Dr. Waleed K .Jawad, Jamal H. Mohamed, “Studying the Effect of Punch Nose Radius on Deep Drawing Operation”,*Eng. &Tech.*Vol.No .26,pp55-73, (2008)
- [2] G. Venkateswarlu, M. J. Davidson and G. R. N. Tagore, “Influence of process parameters on the cup drawing of aluminium 7075 sheet *International Journal of Engineering, Science and Technology* Vol. 2, No. 11, pp. 41-49, (2010)
- [3] Y. Marumo, H. Saiki, L Ruan, “Effect of sheet thickness on deep drawing of metal foils”, *Journal of Achievements in Materials and Manufacturing Engineering* Vol.20 Issues 1-2, (2007)
- [4] M. Ahmetoglu, T. R. Broek, G. Kinzel, T. Altan, —Control of Blank Holder Force to Eliminate Wrinkling and Fracture in Deep-Drawing Rectangular Parts *Annals of the CIRP* Vol. 44/1/1995
- [5] H. Gharib, A.S. Wifi, M. Younan, A. Nassef, “Optimization of the blank holder force in cup drawing”,*Journal of Achievements in Materials and Manufacturing Engineering*, Volume 18, ISSUE 1-2 September–October 2006
- [6] W.M. Chan, H.I. Chew, H.P. Lee, B.T. Cheok , “Finite element analysis of spring-back of V-bending sheet metal forming processes”,*Journal of Materials Processing Technology* Vol.148 pp 15–24, (2004)
- [7] Keeler, S.P.,*Sheet Met. Indust*,Vol.42. pp.683,1965
- [8] Kalpakjain, “*Manufacturing Processes for Engineering Materials*”(Pearson Education, 2007)
- [9] Z. Marciniak, K. Kuczynski, “ Limit strains in the process of stretch-forming sheet metal”*Int. J. Mech. Sci.* 9 (1967) 609–620.
- [10] S.P. Keeler, “Circular grid system—A valuable aid for evaluating sheet metal formability”,*Society of Automotive Engineers Technical Paper No. 680092*, New York, 1968.
- [11] Z. Marciniak, K. Kuczynski, T. Pokora, “Influence of the plastic properties of a material on the forming limit diagram for sheet metal in tension”,*Int. J. Mech. Sci.* 15,pp 789–805,1973.
- [12] A.K. Ghosh, S.S. Hecker, “Stretching limits in sheet metals:In-plane versus out-of-plane deformation”,*Metall. Trans.* 5,pp 2161–2164,(1974)
- [13] S.S. Hecker, “Experimental studies of sheet stretchability, Formability: Analysis, Modeling and Experimentation”, *Proceedings October 1977 AIME:ASM Symposium*, —The Metallurgical Society of the American Institute of Mining, Metallurgical and Petroleum Engineers” pp. 150–182 New York, 1978.
- [14] S.S. Hecker, “Simple technique for determining forming limit curves”, *Sheet Met. Ind.* 52, pp671–676 (1975).
- [15] D. Lee, F. Zaverl Jr., “Neck growth and forming limits in sheet metals” ,*Int. J. Mech. Sci.* 24 (3) pp.157–173(1982).
- [16] FahrettingOzturk and Daeyong Lee, “Analysis of forming limits using ductile fracture criteria”, *Journal of Material Process Technology* Vol. No. 147, Issue – 3, pp- 397- 404, 2004.
- [17] Li K P, Carden W.P and Wagoner R H , “Simulation of Spring Back”, *International Journal of Mechanical Science*, Vol. No. -45, Issue – 1 , pp-103-122, 2002



- [18] Carden W.D., Geng L.M, Matlock D.K., and Wagoner , “Measurement of Spring back”, International Journal of Mechanical Science, Vol. No. -44, Issue- 1, pp.- 79- 101, 2002
- [19] FlavioCimolin, Roberto Vadori and Claudio, “Springback compensation in deep drawing application”, Journal of Meccanica , Vol. No.- 43, Issue- 2, PP. 101-113, 2008.